


特 許 協 力 条 約

PCT

国際予備審査報告

(法第12条、法施行規則第56条)  
[PCT36条及びPCT規則70]



出願人又は代理人 の書類記号 FP-8337PCT	今後の手続きについては、国際予備審査報告の送付通知(様式PCT/ IPEA/416)を参照すること。	
国際出願番号 PCT/JP03/03398	国際出願日 (日.月.年) 20.03.2003	優先日 (日.月.年) 25.03.2002
国際特許分類(IPC) Int.Cl <sup>7</sup> D03D15/12、D03D15/00、D02G3/04		
出願人(氏名又は名称) 鐘淵化学工業株式会社		

1. 国際予備審査機関が作成したこの国際予備審査報告を法施行規則第57条(PCT36条)の規定に従い送付する。
2. この国際予備審査報告は、この表紙を含めて全部で 4 ページからなる。  <input type="checkbox"/> この国際予備審査報告には、附属書類、つまり補正されて、この報告の基礎とされた及び/又はこの国際予備審査機関に対してした訂正を含む明細書、請求の範囲及び/又は図面も添付されている。 (PCT規則70.16及びPCT実施細則第607号参照) この附属書類は、全部で _____ ページである。
3. この国際予備審査報告は、次の内容を含む。  I <input checked="" type="checkbox"/> 国際予備審査報告の基礎 II <input type="checkbox"/> 優先権 III <input type="checkbox"/> 新規性、進歩性又は産業上の利用可能性についての国際予備審査報告の不作成 IV <input type="checkbox"/> 発明の単一性の欠如 V <input checked="" type="checkbox"/> PCT35条(2)に規定する新規性、進歩性又は産業上の利用可能性についての見解、それを裏付けるための文献及び説明 VI <input type="checkbox"/> ある種の引用文献 VII <input type="checkbox"/> 国際出願の不備 VIII <input type="checkbox"/> 国際出願に対する意見

国際予備審査の請求書を受理した日 01.10.2003	国際予備審査報告を作成した日 15.04.2004	
名称及びあて先 日本国特許庁(IPEA/JP) 郵便番号100-8915 東京都千代田区霞が関三丁目4番3号	特許庁審査官(権限のある職員) 山崎 利直 印	4S 3233
電話番号 03-3581-1101 内線 3430		

## I. 国際予備審査報告の基礎

1. この国際予備審査報告は下記の出願書類に基づいて作成された。(法第6条(PCT14条)の規定に基づく命令に  
 応答するために提出された差し替え用紙は、この報告書において「出願時」とし、本報告書には添付しない。  
 PCT規則70.16, 70.17)

☒ 出願時の国際出願書類

- |                                     |         |        |                      |
|-------------------------------------|---------|--------|----------------------|
| <input type="checkbox"/> 明細書        | 第 _____ | ページ、   | 出願時に提出されたもの          |
| <input type="checkbox"/> 明細書        | 第 _____ | ページ、   | 国際予備審査の請求書と共に提出されたもの |
| <input type="checkbox"/> 明細書        | 第 _____ | ページ、   | 付の書簡と共に提出されたもの       |
|                                     |         |        |                      |
| <input type="checkbox"/> 請求の範囲      | 第 _____ | 項、     | 出願時に提出されたもの          |
| <input type="checkbox"/> 請求の範囲      | 第 _____ | 項、     | PCT19条の規定に基づき補正されたもの |
| <input type="checkbox"/> 請求の範囲      | 第 _____ | 項、     | 国際予備審査の請求書と共に提出されたもの |
| <input type="checkbox"/> 請求の範囲      | 第 _____ | 項、     | 付の書簡と共に提出されたもの       |
|                                     |         |        |                      |
| <input type="checkbox"/> 図面         | 第 _____ | ページ/図、 | 出願時に提出されたもの          |
| <input type="checkbox"/> 図面         | 第 _____ | ページ/図、 | 国際予備審査の請求書と共に提出されたもの |
| <input type="checkbox"/> 図面         | 第 _____ | ページ/図、 | 付の書簡と共に提出されたもの       |
|                                     |         |        |                      |
| <input type="checkbox"/> 明細書の配列表の部分 | 第 _____ | ページ、   | 出願時に提出されたもの          |
| <input type="checkbox"/> 明細書の配列表の部分 | 第 _____ | ページ、   | 国際予備審査の請求書と共に提出されたもの |
| <input type="checkbox"/> 明細書の配列表の部分 | 第 _____ | ページ、   | 付の書簡と共に提出されたもの       |

2. 上記の出願書類の言語は、下記に示す場合を除くほか、この国際出願の言語である。

上記の書類は、下記の言語である \_\_\_\_\_ 語である。

- ☐ 国際調査のために提出されたPCT規則23.1(b)にいう翻訳文の言語  
☐ PCT規則48.3(b)にいう国際公開の言語  
☐ 国際予備審査のために提出されたPCT規則55.2または55.3にいう翻訳文の言語

3. この国際出願は、ヌクレオチド又はアミノ酸配列を含んでおり、次の配列表に基づき国際予備審査報告を行った。

- ☐ この国際出願に含まれる書面による配列表  
☐ この国際出願と共に提出された磁気ディスクによる配列表  
☐ 出願後に、この国際予備審査(または調査)機関に提出された書面による配列表  
☐ 出願後に、この国際予備審査(または調査)機関に提出された磁気ディスクによる配列表  
☐ 出願後に提出した書面による配列表が出願時における国際出願の開示の範囲を超える事項を含まない旨の陳述書の提出があった  
☐ 書面による配列表に記載した配列と磁気ディスクによる配列表に記載した配列が同一である旨の陳述書の提出があった。

4. 補正により、下記の書類が削除された。

- ☐ 明細書 第 \_\_\_\_\_ ページ  
☐ 請求の範囲 第 \_\_\_\_\_ 項  
☐ 図面 図面の第 \_\_\_\_\_ ページ/図

5. ☐ この国際予備審査報告は、補充欄に示したように、補正が出願時における開示の範囲を越えてされたものと認められるので、その補正がされなかったものとして作成した。(PCT規則70.2(c) この補正を含む差し替え用紙は上記1.における判断の際に考慮しなければならない、本報告に添付する。)

## V. 新規性、進歩性又は産業上の利用可能性についての法第12条(PCT35条(2))に定める見解、それを裏付ける文献及び説明

## 1. 見解

新規性(N)	請求の範囲	1, 2	有
	請求の範囲		無
進歩性(IS)	請求の範囲		有
	請求の範囲	1, 2	無
産業上の利用可能性(IA)	請求の範囲	1, 2	有
	請求の範囲		無

## 2. 文献及び説明(PCT規則70.7)

文献1: JP 2593985 B2 請求項1、【0041】  
 文献2: JP 2001-535644 A 第3頁第14行~第17行  
 文献3: JP 2593986 B2 請求項1、【0010】、【0040】

- ・請求項1, 2
- ・文献1, 2

上記文献1の実施例5には、アクリロニトリル49重量%、ハロゲン含有ビニル系単量体51重量%を含む単量体混合物を重合させてなるアクリル系共重合体に、該共重合体に対して50重量%のSb化合物を含有させた繊維70重量部と、綿30重量部とを含む難燃繊維複合体を用いた織物について記載されている。

本願明細書を参酌するに、アクリル系共重合体と混合させる繊維として綿及びレーヨンを選択し、かつ本願請求項1に記載の繊維(a-1)と繊維(a-2)の配合比を満たすならば、本願請求項1に記載の伸長率を満たすものと認められるので、上記文献1の実施例5に記載の難燃繊維複合体についても、本願請求項1に記載の伸長率を満たすものと認められる。

また、文献1の実施例6には、モダアクリル繊維100%の紡績糸を緯糸に、綿100%の紡績糸を経糸に用いた交織平織織物について記載されているし、文献2には、セルロース系繊維と含ハロゲン難燃繊維を用いた交織織物がセルロース系繊維の特徴を活かすことができる旨記載されているから、セルロース系繊維の特徴を活かすことに着想して、上記文献1に記載の難燃繊維複合体と綿等の繊維を用いて交織平織織物を製織することは、当業者が容易になし得ることであると認められる。

- ・請求項1, 2
- ・文献2, 3

上記文献3の実施例5には、アクリロニトリル49重量%、ハロゲン含有ビニル系単量体51重量%を含む単量体混合物を重合させてなるアクリル系共重合体に、該共重合体に対して50重量%のSb化合物を含有させた繊維70重量部と、綿30重量部とを含む難燃繊維複合体を用いた織物について記載されている。

本願明細書を参酌するに、アクリル系共重合体と混合させる繊維として綿及びレーヨンを選択し、かつ本願請求項1に記載の繊維(a-1)と繊維(a-2)の配合比を満たすならば、本願請求項1に記載の伸長率を満たすものと認められるので、上記文献3の実施例5に記載の難燃繊維複合体についても、本願請求項1に記載の伸長率を満たすものと認められる。

また、文献3の実施例6には、モダアクリル繊維100%の紡績糸を緯糸に、綿100%の紡績糸を経糸に用いた交織平織織物について記載されているし、文献2に

補充欄 (いずれかの欄の大きさが足りない場合に使用すること)

## 第 V 欄の続き

は、セルロース系繊維と含ハロゲン難燃繊維を用いた交織織物がセルロース系繊維の特徴を活かすことができる旨記載されているから、セルロース系繊維の特徴を活かすことに着想して、上記文献3に記載の難燃繊維複合体と綿等の繊維を用いて交織平織織物を製織することは、当業者が容易になし得ることであると認められる。

Translation

PATENT COOPERATION TREATY

PCT

INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)

PCT/JP2003/003398



Applicant's or agent's file reference FP-8337PCT	<b>FOR FURTHER ACTION</b> See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)	
International application No. PCT/JP2003/003398	International filing date (day/month/year) 20 March 2003 (20.03.2003)	Priority date (day/month/year) 25 March 2002 (25.03.2002)
International Patent Classification (IPC) or national classification and IPC D03D 15/12, 15/00, D02G 3/04		
Applicant KANEKA CORPORATION		

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.

2. This REPORT consists of a total of 5 sheets, including this cover sheet.

☐ This report is also accompanied by ANNEXES, i.e., sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of \_\_\_\_\_ sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☐ Certain observations on the international application

Date of submission of the demand 01 October 2003 (01.10.2003)	Date of completion of this report 15 April 2004 (15.04.2004)
Name and mailing address of the IPEA/JP	Authorized officer
Facsimile No.	Telephone No.

# INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/JP2003/003398

## I. Basis of the report

### 1. With regard to the elements of the international application:\*

- ☒ the international application as originally filed
- ☐ the description:  
 pages \_\_\_\_\_, as originally filed  
 pages \_\_\_\_\_, filed with the demand  
 pages \_\_\_\_\_, filed with the letter of \_\_\_\_\_
- ☐ the claims:  
 pages \_\_\_\_\_, as originally filed  
 pages \_\_\_\_\_, as amended (together with any statement under Article 19  
 pages \_\_\_\_\_, filed with the demand  
 pages \_\_\_\_\_, filed with the letter of \_\_\_\_\_
- ☐ the drawings:  
 pages \_\_\_\_\_, as originally filed  
 pages \_\_\_\_\_, filed with the demand  
 pages \_\_\_\_\_, filed with the letter of \_\_\_\_\_
- ☐ the sequence listing part of the description:  
 pages \_\_\_\_\_, as originally filed  
 pages \_\_\_\_\_, filed with the demand  
 pages \_\_\_\_\_, filed with the letter of \_\_\_\_\_

### 2. With regard to the language, all the elements marked above were available or furnished to this Authority in the language in which the international application was filed, unless otherwise indicated under this item.

These elements were available or furnished to this Authority in the following language \_\_\_\_\_ which is:

- ☐ the language of a translation furnished for the purposes of international search (under Rule 23.1(b)).
- ☐ the language of publication of the international application (under Rule 48.3(b)).
- ☐ the language of the translation furnished for the purposes of international preliminary examination (under Rule 55.2 and/or 55.3).

### 3. With regard to any nucleotide and/or amino acid sequence disclosed in the international application, the international preliminary examination was carried out on the basis of the sequence listing:

- ☐ contained in the international application in written form.
- ☐ filed together with the international application in computer readable form.
- ☐ furnished subsequently to this Authority in written form.
- ☐ furnished subsequently to this Authority in computer readable form.
- ☐ The statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.
- ☐ The statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished.

### 4. ☐ The amendments have resulted in the cancellation of:

- ☐ the description, pages \_\_\_\_\_
- ☐ the claims, Nos. \_\_\_\_\_
- ☐ the drawings, sheets/fig \_\_\_\_\_

### 5. ☐ This report has been established as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed, as indicated in the Supplemental Box (Rule 70.2(c)).\*\*

\* Replacement sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to this report since they do not contain amendments (Rule 70.16 and 70.17).

\*\* Any replacement sheet containing such amendments must be referred to under item 1 and annexed to this report.

# INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/JP 03/03398

## V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement

### 1. Statement

Novelty (N)	Claims	1, 2	YES
	Claims		NO
Inventive step (IS)	Claims		YES
	Claims	1, 2	NO
Industrial applicability (IA)	Claims	1, 2	YES
	Claims		NO

### 2. Citations and explanations

Document 1: JP 2593985 B2 (claim 1, paragraph [0041])  
 Document 2: JP 2001-535644 A (page 3, lines 14-17)  
 Document 3: JP 2593986 B2 (claim 1, paragraphs [0010]  
 and [0040])

Claims 1 and 2

Documents 1 and 2

Document 1 (example 5) discloses a fabric configured from a flame-retardant fiber composite that comprises 30 parts by weight of cotton and 70 parts by weight of fibers comprising an acrylic copolymer, which is obtained by polymerizing a monomer mixture that comprises 49% by weight of an acrylonitrile and 51% by weight of a halogen-containing vinyl monomer, and an Sb compound at a ratio of 50% by weight in relation to said copolymer.

Consideration of the description of this application suggests that if cotton or rayon is selected as the fiber that is mixed with the acrylic copolymer, and if the fiber (a-1) to fiber (a-2) mixture ratio that is set forth in claim 1 of this application is fulfilled, the resulting invention will exhibit the elongation rate that is set forth in claim 1 of this application; therefore, the flame-retardant fiber composite that is disclosed in document 1 (example 5) is considered to exhibit the

elongation rate that is set forth in claim 1 of this application.

In addition, document 1 (example 6) indicates an interlaced plain-woven cloth, which is configured from horizontal fibers of a spun yarn that comprises 100% modacrylic fibers and vertical fibers of a spun yarn that comprises 100% cotton, and document 2 indicates that an interlaced cloth comprising cellulose fibers and halogen-containing fire-resistant fibers exhibits the characteristics of the cellulose fibers. Therefore, it is considered to be easy for a person skilled in the art to produce an interlaced plain-woven cloth that comprises the fire-resistant fiber composite disclosed in document 1 and fibers of cotton or the like with the expectation that the cloth will exhibit the characteristics of the cellulose fibers.

Claims 1 and 2

Documents 2 and 3

Document 3 (example 5) discloses a fabric configured from a flame-retardant fiber composite that comprises 30 parts by weight of cotton and 70 parts by weight of fibers comprising an acrylic copolymer, which is obtained by polymerizing a monomer mixture that comprises 49% by weight of an acrylonitrile and 51% by weight of a halogen-containing vinyl monomer, and an Sb compound at a ratio of 50% by weight in relation to said copolymer.

Consideration of the description of this application suggests that if cotton or rayon is selected as the fiber that is mixed with the acrylic copolymer, and if the fiber (a-1) to fiber (a-2) mixture ratio that is set forth in claim 1 of this application is fulfilled, the resulting invention will exhibit the elongation rate that is set forth in claim 1 of this application; therefore, the flame-retardant fiber composite that is disclosed in



INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No.

PCT/JP 03/03398

document 3 (example 5) is considered to exhibit the elongation rate that is set forth in claim 1 of this application.

In addition, document 3 (example 6) indicates an interlaced plain-woven cloth, which is configured from horizontal fibers of a spun yarn that comprises 100% modacrylic fibers and vertical fibers of a spun yarn that comprises 100% cotton, and document 2 indicates that an interlaced cloth comprising cellulose fibers and halogen-containing fire-resistant fibers exhibits the characteristics of the cellulose fibers. Therefore, it is considered to be easy for a person skilled in the art to produce an interlaced plain-woven cloth that comprises the fire-resistant fiber composite disclosed in document 3 and fibers of cotton or the like with the expectation that the cloth will exhibit the characteristics of the cellulose fibers.